

## Acryl

Special coat 2K CP 88 Premium 2:1



**2K Acryl** coat is meant for creating coats on a number of surfaces (steel, aluminium and polymers). The two-component technology allows you to achieve the effect of gloss surface, or matt surface if **CP 003** is added. By using **Fleet Aditiv MIX 002**, you are able to coat large surfaces. It has a very short drying time and UV resistance. The coat is fluorinated.

Use according to Directive 2004/42/WE - coatings designed for application as topcoats requiring special properties - subcategory (e).

**The product has a 10-year coating guarantee\*.**

*\*) Further details available at our website <http://www.multichem.pl>.*

Unit	Packaging	Collective (box)
1 L*		3 pcs
3,5 L*		2 pcs

*\*) Sizes available for specific toners is presented in the table (on the next page).*

### Output:

20-30 µm for each layer  
9 m<sup>2</sup>/1 L

### Spray viscosity:

21-24 s DIN Cup 4 mm

### VOC:

2004/42/WE/IIb(e)(840) 840

### Shelf life under normal storage conditions minimum:

24 months in an original closed package



**100 parts Acryl (CP 88 PREMIUM),**  
**50 parts** of hardener **CP 285,**  
**10-20 parts** of thinner **CP 040.**



Two full versions or until full coverage is achieved. By using **Fleet Aditiv MIX 002** you can coat large surfaces.

Spray gun\*. Gravity nozzle: **1.2-1.4 mm.** Suction nozzle: **1.4-1.6 mm.\***

*\* Use high pressure equipment and HVLP. Pressure as recommended by the gun manufacturer.*



Evaporation between the layers (20°C, 65% H.R.):  
**5 min.**



Drying time 20°C, relative humidity 65%: **12 h\***  
Drying time 60°C, relative humidity 65%: **30 min**

*\* Tested with hardener CP 285.*

*The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognise the guarantee and all claims, the user shall use the technologies and techniques for using the Products - according to the technical data sheet and execute the sample spray prior to target painting.*